

ID Material: 66
Rble: R. Antich
Revision: 6
Last updated: 13/11/2023

SF-MC2

SF-MC2 is a high performance metal free material, with a high friction coefficient. It has a high percentage of aramid fibre. It can be considered as an alternative for sintered metal materials and offers many advantages. It resists high energy inputs and is suitable for both dry and oil-immersed applications. It is not abrasive to the counter material, and it's noiseless while operating. It resists high surface pressures. The wear rate is low even at high temperatures. SF-MC2 is available in thicknesses from 0.4mm to 7.5mm. Similar to SF-BU but with higher friction coefficient.

Material data

Friction Properties (according graphics)

Static Friction Coefficient (15bar, from box):	0.40±0.05	μ
Static Friction Coefficient (15bar, 100°C):	0.45±0.05	μ
Dynamic Friction Coefficient:	see charts	
Wear Rate:	see charts	
T° Fading:	>400	°C

Physical properties

Hardness (DIN53505):	85±5	Shore-D
Specific Gravity (ASTM D792):	1.30±0.05	gr/cm3
Thermal Conductivity (ASTM E1952):	0.25±0.01	W/m²K

Mechanical properties

Tensile Strength (ASTM D638):	70±5	N/mm²
Compressive Strength (ISO 844:2014):	306±10	N/mm²
Burst Resistant (200 x 137 x 3,5) 200°C:	18200±100	RPM
Poisson Coefficient (ASTM D638):	0.27±0.03	
Young Modulus (ASTM D638):	7260±100	N/mm²

Recommended Working Values

T° Max. Continuous Operation:	360	°C
T° Max. Intermittent Operation:	400	°C

Material type : Paper Friction

Appearance / Formats



Applications

Car / motorcycle competition clutches - Clutch buttons - Heavy vehicle clutches - Micellaneous industrial brakes / clutches

Price Level : € € €

Reach (EC)1907/2023 - RoHS 2015/863/EU : Compliance

Others

Recommended Mating Surface:	Perlitic cast iron, hardness HB150-200
Recommended Adhesives:	Thermosetting adhesive
Oil Resistant:	Yes

